


Araldite[®] 2050

Fast bonding. Anytime. Anywhere.

Speed up bonding operations under any conditions of cold temperatures, saltwater and humidity



Key benefits

- > Ultra-fast curing
- > From -20 to 25°C without additional heat
- > Under water and in humid areas
- > Virtually no surface preparation
- > Outstanding adhesion on dissimilar substrates
- > Excellent ageing and weathering resistance
- > Temperature resistance up to 120°C

SONDI




COLD AND WET

Araldite²⁰⁵⁰

Fast bonding. Anytime. Anywhere.

Typical product characteristics


Pot life at RT	2 min
Fixture time at RT	9 min
Processing temperature	-20 to 25°C
Maximum service temperature	120°C
Tensile strength	40 MPa
Tensile modulus	1 700 MPa
Elongation at break	ca. 10%



Fixture time at different temperatures

Lap Shear Strength after ageing

Lap Shear Strength at 23°C ISO 4587



Legal information All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries. Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials (Guangdong) Ltd. ("Huntsman"). The following supercedes Buyer's documents. While the information and recommendations included in this publication are, to the best of Huntsman Advanced Materials (Guangdong) Ltd. ("Huntsman"). The following supercedes Buyer's documents. While the information and recommendations included in this publication, or Huntsman as A PEPRESENTATION OR WARRANTY OF MARRANTY OF MARRANTY OF DESCONSTRUED AS A PEPRESENTATION OR WARRANTY OF SON RWICES, NOR MULED, INCLUDING, BUT NOT LUMITED TO ANY WARRANTY OF MARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTS OF CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES. No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Data and results are based on controlled conditions and/or lab work. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property right. The Product may be or become hazardous. Buyer should (i) obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product market advacts upper storage in recumate bala sheets and recumate bala sh standards relating to the handling, use, storage, distribution and disposal of and exposure to the Product. Please note that products may differ from country to country. If you have any queries, kindly contact your local Huntsman representative © 2019 Huntsman Corporation. All rights reserved. Ref. No. AdMat Araldite® 2050_03.19_EN_EU