



Scotch-Weld™ Epoxy Adhesive DP760

Product Data Sheet

June 2016

Supersedes: August 2013

Product Description

3M™ Scotch-Weld™ DP760 epoxy adhesive is a non-sag, two-part room temperature curing adhesive designed for use when high temperature resistance is required.

Key Features

- Epoxy adhesive
- 2:1 mix ratio
- Non sagging paste for an ease of use
- High temperature resistance

Physical Properties

	BASE	ACCELERATOR
Base Resin	Modified Epoxy	Modified Amine
Colour	White	White
Density⁽¹⁾	1.24	0.84
Viscosity	Non sagging Paste	Non sagging Paste
Mix Ratio - by volume - by weight	100 parts 100 parts	50 parts 32 parts
Work Life⁽²⁾ 5g 10g	90 min 70 min	

(1) Density measured using pycnometer at 23°C.

(2) Maximum time that adhesive can remain useable after a mix of 5 or 10g at 23°C.

Performance Characteristics

Overlap Shear (MPa)⁽³⁾

Aluminium 2024T3 FPL Etched	Cycle 1 7 days at 23°C	Cycle 2 120 min at 65°C
- 55 ± 3 °C	-	21.7 (CF)
23 ± 2 °C	32 (CF)	31.5 (CF)
120 ± 2 °C	14.8 (CF)	14.5 (CF)
150 ± 2 °C	9.7 (CF)	8.7 (CF)

(3) Overlap shear values measured using EN-2243-1; adhesive allowed to cure for 7 days at 23°C or 120 minutes at 65 °C; 12.5 mm overlap; 90-150 µm bond line thickness; samples pulled at 2.5 mm/min s; all samples are FPL Etched Aluminium 2024T3 1.6 mm thick

Failure modes:

AF: adhesive failure CF: cohesive failure SF: substrate failure

Floating Roller Peel (N/ 25 mm width)⁽⁴⁾

Aluminium 2024T3 FPL Etched	DP 760
23°C	110 (CF)

4) Floating roller peel values measured using EN 2243-2; adhesives allowed to cure for 120 minutes at 65°C; 25 mm wide samples; 90-150 µm bond line thickness; samples pulled at 150 mm/min; aluminium surfaces etched; substrates used were 1.6 mm thick and 0.5 mm thick aluminium.

Failure modes:

AF: adhesive failure CF: cohesive failure SF: substrate failure

Directions For Use

1. To obtain the highest strength structural bonds, paint, oxide films, oils, dust, mould release agents, and all other surface contaminants must be removed completely.

The amount of surface preparation depends on the required bond strength and environmental aging resistance desired by user. For suggested surface preparations on common substrates, see the section on surface preparation.

2. Mixing

For Duo-Pak Cartridges

Store cartridges with cap end up allowing any air bubbles to rise towards the tip. To use, simply insert the cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Then remove the cap and expel a small amount of adhesive to ensure material flows freely from both sides of cartridge. For automatic mixing, attach an EPX mixing nozzle to the cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after obtaining a uniform colour

Directions For Use

3. Apply adhesive and join surfaces within the open time listed for the specific product. Larger quantities and/or higher temperatures will reduce this working time.
4. Allow adhesive to cure at 16°C or above until completely firm. Applying heat up to 66°C will increase cure speed.
5. Keep parts from moving during cure. Apply contact pressure or fixture in place if necessary. The optimum bond line thickness ranges from 100 to 500 µm; shear strength will be maximized with thinner bond lines, while peel strength reaches a maximum with thicker bond lines.
6. Excess uncured adhesive can be cleaned up with ketone type solvents.*

***Note:**

When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use .

Surface Preparation

The following cleaning methods are suggested for common surfaces:

Steel & Aluminium:

1. Wipe free of dust and dirt with pure solvent such as acetone or isopropyl alcohol.*
2. Sandblast or abrade using clean fine grit abrasives.
3. Wipe again with clean solvent to remove loose particles.*
4. When using a primer, apply within 4 hours after surface preparation.

Where humid environments are likely to be encountered by metallic substrates, we recommend additional priming with 3M™ Scotch-Weld™ 3901. Alternatively, chemical conversion coating techniques combined with priming can offer the best durability.

Plastics/Rubbers:

1. Wipe with isopropyl alcohol.*
2. Abrade using fine grit abrasives.
3. Wipe with isopropyl alcohol.*

Glass:

1. Solvent wipe surface using acetone or MEK.*
 2. Apply a thin coating of a silane adhesion promoter to the glass surfaces to be bonded and allow to dry completely before bonding.
-

Storage & Shelf Life

Store temperature at 4 °C max and product in original packaging will ensure the shelf life. Do not freeze. Allow product to reach room temperature prior to use.

The product can be stored up to 24 months after production

Note: The shelf life may be shortened if the original packaging is not properly sealed or stored in an environment with high temperatures or humidity.

Precautionary Information

Refer to product label and Material Safety Data Sheet for health and safety information before using the product.
For information please contact your local 3M Office.
www.3M.com

For Additional Information

To request additional product information or to arrange for sales assistance, go to www.3M.be/bonding or www.3M.nl/bonding

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M and Scotch-Weld are trademarks of the 3M Company.



Industrial Adhesives & Tapes Division
3M Belgium
Hermeslaan 7
1831 Diegem
Belgium

Industrial Adhesives & Tapes Division
3M Nederland
Molengraafsingel 29
2629 JD Delft
Nederland